


1-800-383-7323 USA/CAN www.energizer.com

AΑ

# ENERGIZER NH15-2300



# **Industry Standard Dimensions**



# **Discharge Characteristics**

#### Typical Performance at 21°C (70°F) 1.4 1.3 230 mA Cell Voltage 1.1 1.0 (0.1C)460 mA (0.2C)1.0 0.9 0 3 9 12 6 Hours of Discharge 1.4 1.3 1150 mA Cell Voltage 1.2 (0.5C) 2300 mA 1.1 (1.0C)4600 mA 1.0 (2.0C) 0.9 0.0 0.5 2.0 2.5 1.0 1.5 Hours of Discharge

Classification: Chemical System: Designation: Nominal Voltage: Rated Capacity: Typical Weight: Typical Volume: Terminals: Jacket: Rechargeable Nickel-Metal Hydride (NiMH) ANSI-1.2H2 1.2 Volts 2300 mAh\* at 21°C (70°F) 30.0 grams (1.1 oz.) 8.3 cubic centimeters (0.5 cubic inch) Flat Contact Plastic

**Specifications** 

\* Based on 460 mA (0.2C rate) continuous discharge to 1.0 volts.

### **Internal Resistance:**

The internal resistance of the cell varies with state of charge, as follows:

Cell ChargedCell 1/2 Discharged30 milliohms40 milliohms(tolerance of ±20% applies to above values)

## AC Impedance (no load):

The impedance of the charged cell varies with frequency, as follows:

Frequency (Hz) 1000 Impedance (milliohms) (charged cell) 12

Above values based on AC current set at 1.0 ampere. Value tolerances are  $\pm 20\%.$ 

### **Operating and Storage Temperatures:**

To maintain maximum performance, observe the following general guidelines regarding environmental conditions:

Charge:	0°C to 40°C (32°F to 104°F)
Discharge:	0°C to 50°C (32°F to 122°F)
Storage:	-20°C to 30°C (-4°F to 86°F)
Humidity:	65±20%

**NOTE:** Operating at extreme temperatures, will significantly impact battery cycle life.

### Important Notice

This data sheet contains typical information specific to products manufactured at the time of its publication. © Energizer Holdings, Inc. - Contents herein do not constitute a warranty.